



Soil





Soil

Woven on an air jet loom, piece dyed and 60% sustainable - RPET- make this textile unique in its kind. It is soft, durable and has a fine woven structure. Soil has a light melange and matt aspect and is part of our www.wovenbottles.com collection.

Soil fits for all types of upholstery and will make your chair, sofa and bed look more luxurious and exclusive. Please note that during use a light wooly or hairy look can appear, this has no further influence on the durability of this sustainable textile.

Soil has been developed with comfort in mind, usable for many years and easy to clean with mainly a damp cloth. This soft textile is machine-washable 30 degrees Celsius and the 100% RPET non-woven backing creates this extra comfortable and thick handfeel.

Available from stock in a wide range of trendy, modern and commercial colours.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

Fabrra Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-quality, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

Composition

/ faceside 60%RPET 40%PES
/ backside 100%RPET
/ flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery




anthracite 67




army 14




blush 92



carmine 36



coffee 81



darkgrey 68




eucalyptus 193



hazel 96




hunter 156



indigo 90



lilac 70




liver 10

Please note: colours may vary according to your screen settings.



natural 01



niagara 158



ocre 23



sage 203




sepia 176




steel 149



taupe 12



turquoise 44



zinc 167


Please note: colours may vary according to your screen settings.

Soil - Article passport
A partly sustainable, soft, durable, fine woven article with a light multi-coloured aspect
Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	60%RPET 40%PES	
Composition backside	100%RPET	
Bonding	non-woven	
Statistic code	54079200	
Dyeing method	piece dyed	
Available colours	21	
Packaging	transparent plastic	






Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4-5		min. 4	min.5	B-C
	middle colours	CTL	grade	4-5		min. 4	min.5	B-C
	dark colours	CTL	grade	4-5		min. 4	min.5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 497							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	2.110	1.277	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	187,6	150,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,0	2,8	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	56,5	41,9	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	0,0	n/a	n/a	A/A
<div></div> <p>- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.</p>								

