



Cyber



OEKO-TEX®
CONFIDENCE IN TEXTILES



FABRAA[®]
fabrics with a conscience



Cyber

This new and luxurious RPET woven upholstery textile is in our www.wovenbottles.com collection.

Woven on an air jet loom with micro-chenille yarns, these yarns provide a voluminous, chunky and comfortable handfeel. Cyber is piece dyed and is suitable for all types of upholstery, such as loose covers, tight fitted or buttoned.

The face-side exists of 96% RPET and 4% virgin nylon and the backing is made from 100% RPET. It is soft and sustainable and besides that also strong and durable.

All certifications are available and available in a wide range of contemporary, commercial and trendy colours from stock.

For loose covers it is also nice to mention that Cyber is machine-washable at 30 degrees Celsius*.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Fabrra Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-quality, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

Composition

/ faceside 96%RPET 4%NY
/ backside 100%RPET
/ flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



beige 05



blush 92




clay 84




desert 109



forest 162



graphite 66



grey 65



liver 10



mustard 06



natural 01



niagara 158



pearl 106

Please note: colours may vary according to your screen settings.



plumb 168 (new colour)



royalblue 47




shell 196



slate 87



taupe 12



thyme 206

Please note: colours may vary according to your screen settings.

Cyber - Article passport


A fabric from micro chenille yarns with extra voluminous and comfortable handfeel.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	96%RPET 4%NY	
Composition backside	100%RPET	
Bonding	non-woven	
Statistic code	54075200	
Dyeing method	piece dyed	
Available colours	18	
Packaging	transparent plastic	






Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	90.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	<div></div> <div>BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette</div>	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 143							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 590							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.878	1.028	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	159,0	74,1	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,7	1,3	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	49,0	43,7	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	-1,2	n/a	n/a	A/A
    				- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.				

OEKO-TEX®
CERTIFIED BY TESTES



FABRAA®
fabrics with a conscience

Textafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@fabraa.com
www.fabraa.com

nov 2022