



Fjord



**FABRAA**<sup>F</sup>  
fabrics with a conscience



# Fjord

Fjord is a very stylish sustainable upholstery fabric in our [www.fabraa.com](http://www.fabraa.com) collection. It is made from yarns of 100% recycled polypropylene. Post-industrial (rest material) has been used for the production of this soft upholstery fabric.

Fjord is a yarn dyed, woven fabric with a slightly irregular pattern, which gives a very fashionable look on your furniture. Fitted, buttoned or loose upholstery, everything is possible. It is your choice, as we are sure that it will look magnificent either way.

The product development team has chosen for a natural toned collection with just a few deeper shades. The colors of Fjord therefore match the current interior fashion trends and can easily be combined with our other sustainable collections.

Fjord passes all tests, so we can assure you of its good performance and durability. The backside is slightly brushed to give more body to this fabric. One of the characteristics of polypropylene is that stains are easy to remove. If needed, this fabric is also machine-washable at 30 degrees Celsius, so it will maintain the natural and fresh look anyway.

- This article has been tested practical, chemical and technical, if during use as certain hairiness appears, please note that it can easily be taken away with a pilling machine.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

*Fabraa Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-quality, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.*

## Composition

/ faceside 100%RPP  
/ backside n/a  
/ flatweave

\*R=recycled

## Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



ashgrey 40



brass 170



brick 128



brown 15



clay 84



desert 109



ecru 102



forest 162



graphite 66



lightgrey 60



linen 110



liver 10

Please note: colours may vary according to your screen settings.






mustard 06




natural 01




sage 203



slate 87



steel 149



taupe 12



teal 198



wood 108

Please note: colours may vary according to your screen settings.


Fjord - Article passport

A very stylish sustainable fabric with a natural look and feel.  
Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%RPP	
Composition backside	n/a	
Bonding / Coating	n/a	
Statistic code	54075300	
Dyeing method	yarn dyed	
Available colours	20	
Packaging	transparent plastic	






Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	25.000		min. 16.000	min. 25.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 320							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	617	648	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	83,0	88,0	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	4,2	4,0	max. 5	max. 4	B/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	1,0	1,0	n/a	n/a	A/A
<div></div> <p>- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.</p>								



**Textafoam b.v.**  
La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle  
The Netherlands

T +31(0)13 534 5934  
F +31(0)13 534 7586  
E info@fabraa.com  
www.fabraa.com