# Wish

# Wish

A touch so pleasantly soft with a natural look, that makes it easy to make a conscious choice for upholstery fabrics. We are proud to present Wish as a part of the www.fabraa.com collection.

Upto 65% of we yarns we use are made of recycled polypropylene and 35% of virgin polyester. The chenille yarns give a matte and soft experience.

The colours of the yarns are carefully developed in a natural and earthy palette, to enhance the ambiance and appearance. If you choose for fitted or loose upholstery for your furniture, either way it will fit perfectly.

This upholstery fabric is machine-washable at 30 degrees Celsius*, which makes it easy to clean and maintain. Quality wise, Wish is strong, durable and meets and exceeds all requirements for upholstery fabrics.

It's everything you've ever wished for in a sustainable upholstery fabric.

- Please note that due to chenille yarns, shading and seat depression are possible.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

*Fabraa* Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-qualty, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

**Composition**

/ faceside 65%RPP 35%PES
/ backside n/a
/ chenille flatweave
*R=recycled

**Suitable for**

sofa's, beds, chairs with fitted and loose fitting upholstery

beige 05

blossom 166

brass 170

charcoal 79

cream 02

darkgrey 68

eucalyptus 193

grey 65

hazel 96

herb 214

lightgrey 60

linen 110

liver 10

natural 01

steel 149

turtle 88

wood 108

## Wish - Article passport

A soft and matte chenille fabric made of mostly sustainable yarns.

Available from stock in a wide range of contemporary and commercial colours.

## Product characteristics

| Productgroup | chenille flatweave |
|---|---|
| Applications | sofa's, beds, chairs with fitted and loose fitting upholstery |
| Composition faceside | 65%RPP 35%PES |
| Composition backside | n/a |
| Bonding / Coating | n/a |
| Statistic code | 58013600 |
| Dyeing method | yarn dyed |
| Available colours | 17 |
| Packaging | transparent plastic |

## Durability specifications

| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RAL GZ 430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
|---|---|---|---|---|---|---|---|---|
| | | | | Dry | Wet | DGM | DGM+ | |
| Abrasion resistance - yarn breakage | DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03 | CTL | cycles | 35.000 | | min. 12.000 | min. 16.000 | B |
| Pilling | DIN EN ISO 12945-2:2000-11. 2000 cycles | CTL | grade | 5 | | min. 3-4 | min. 4 | B |
| Colour fastness to light | DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5 | | | | | | | |
| light colours | | CTL | grade | 5 | | min. 4 | min.5 | B |
| middle colours | | CTL | grade | 5 | | min. 4 | min.5 | B |
| dark colours | | CTL | grade | 5 | | min. 4 | min.5 | B |
| Colour fastness to rubbing | DIN EN ISO 105-X12:2016-11 | | | | | | | |
| light colours | | CTL | grade | 4-5 | 4-5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A |
| middle colours | | CTL | grade | 4-5 | 4-5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A |
| dark colours | | CTL | grade | 4-5 | 4-5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A |
| Ignitability (cigarette test) | BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette | CTL | | passed | | | | |

## Processing specifications

| Minimum workable width in centimeters | ± 138 |
|---|---|
| Roll length in meters | ± 40 |
| Material weight in grams per linear meter | ± 481 |

| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RAL GZ 430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
|---|---|---|---|---|---|---|---|---|
| | | | | Warp | Weft | DGM | DGM+ | |
| Tensile strength | DIN EN ISO 13934-1:2013-08 | CTL | Newton | 980 | 1.160 | min. 350 | min. 400 | A/A |
| Tear growth resistance | DIN EN ISO 13937-3:2000-06 | CTL | Newton | 85,0 | 92,0 | min. 25 | min. 30 | A/A |
| Resistance to seam slippage | DIN EN ISO 13936-2:2004-07. Load 180 N | CTL | mm | 2,5 | 3,5 | max. 5 | max. 4 | A/A |
| Delamination | DIN 53530:1981-02 | CTL | Newton | n/a | n/a | n/a | n/a | n/a |
| Chemical substances | REACH | Centexbel | | passed | | | | |
| | Oeko-Tex, product class II | Centexbel | | certified | | | | |

## Cleaning specifications

| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RAL GZ 430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
|---|---|---|---|---|---|---|---|---|
| | | | | Warp | Weft | DGM | DGM+ | |
| Dimensional change for washing 30 degrees celcius / air drying | DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08 | CTL | % | 0,0 | 0,0 | n/a | n/a | A/A |

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.