



Freya



FABRAA[®]
fabrics with a conscience



Freya

This sustainable luxurious upholstery fabric is woven on a jacquard loom. It is a yarn dyed fabric and the combination is from 96% recycled content, RPET and RPP. The composition in balance with the 'cord' look, makes Freya unique in its kind and will give the sofa, chair, or bed an exclusive look & feel.

Suitable for all types of upholstery and perfect to upholster in many different interiors and styles.

Due to the construction of Freya, we recommend a minimum seam allowance of minimum 1 cm and another kind advice is to overlock all seams for more stability, especially with tight upholstered furniture. For loose fitted upholstery models, please know that Freya is machine-washable at 30 degrees Celsius*.

During usage, a certain hairiness may appear, kindly note that this can be taken away with a pilling razor. This has no further influence on the durability or quality of Freya.

Freya stands for love and sweetness, we hope you experience the same with this super nice textile.

- Always be careful with sharp or rough objects such as watches, buckles, or velcro, as they may damage the fabric.
- When a loop does occur, it can be easily pushed back into the fabric with a blunt object.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Fabreea Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-quality, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

Composition

/ faceside 55%RPET 41%RPP 4%PES
/ backside n/a
/ flatweave

*R=recycled

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery

Freya - Article passport

A sustainable luxurious upholstery fabric woven on a jacquard loom.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	55%RPET 41%RPP 4%PES	
Composition backside	n/a	
Bonding / Coating	n/a	
Statistic code	54077300	
Dyeing method	yarn dyed	
Available colours	8	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	50.000		min. 16.000	min. 25.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 764							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.298	753	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	82,0	416,0	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	4,5	3,7	max. 5	max. 4	B/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-1,0	-2,0	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@fabraa.com
www.fabraa.com